

COOL-LITE® ST BRIGHT SILVER

HIGHLY TRANSPARENT AND AESTHETIC SOLAR PROTECTION FOR THE 2ND SKIN

ST COOL-LITE® BRIGHT SILVER member of solar control coatings family has a convincing, extremely high transparency as well as exceedingly aesthetic and neutral refl ections, whereby it ensures comfort and serenity within the building. The coating is applied to the SGG DIAMANT® extra-white fl oat glass in the standard way.

The SGG COOL-LITE® ST solar protection glass is really versatile: it can be tempered and bent, or heat-strength-ened, or laminated to form multi-layered safety glass, or printed or even enamelled. Its numerous processing possibilities provide huge scope for architectural and technical planning.

This new coating satisfi es all of the demands that are made on versatile processing and it enables a huge variety of possible designs to be created as a result, besides its outstanding aesthetics. This coating has been developed primarily for applying to double-layered facades as glazing for the 2nd skin.

CHARACTERISTICS

Aesthetics: It has a neutral, silvery refl ection that allows translucency and transparency nevertheless.

Combinations: It can be combined with other glasses unproblematically, in order to ensure functions like thermal insulation, soundproofing or protection against injury.

Processing: High level of architectural and technical flexibility.

- It can be tempered or even heatstrengthened as a single sheet of safety glass.

- It can be processed to make multilayered safety glass - even with the coating towards the foil.
- It can also be screen-printed or enamelled in addition. Printing is possible on the glass side as well as the coated side.
- It has a particularly high colour-rendering index, not only in transmission but also in the reflection.

CE-identification marking: This label ensures that the product complies with the EU's applicable quidelines and standards.

APPLICATIONS

- for external layer of double-skin facades
- for windows and façades
- for glass louvres
- for spandrels



COOL-LITE* ST BRIGHT SILVER	Light transmission (TL) [%]	g-value [%]	Ug-value [W/m²K]	RL ext [%]	RL int [%]
6/16/4 on PLANICLEAR Pos. #2 + PLT XN #3	62	52	1.1	32	32

PN-EN 673 & PN-EN 410



SAINT-GOBAIN BUILDING GLASS POLAND

Szklanych Domów 1 42-530 Dąbrowa Górnicza, Poland bgp@saint-gobain.com

www.saint-gobain-building-glass.pl www.glassolutions.pl www.saint-gobain-facade-glass.com



